

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2003-039124

(43)Date of publication of application : 12.02.2003

(51)Int.Cl.

B21D 39/02
B21D 19/08
C22C 21/02
C22C 21/06
C22F 1/05
// C22F 1/00

(21)Application number : 2001-224631

(71)Applicant : KOBE STEEL LTD

(22)Date of filing : 25.07.2001


(72)Inventor : NODA KENJI

(54) HEMMING PROCESS OF ALUMINUM ALLOY PANEL STOCK AND ALUMINUM ALLOY PANEL STOCK

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a hemming process of an aluminum alloy panel stock and an aluminum alloy panel stock for hemming process capable of simultaneously satisfying hemming workability and artificial aging hardenability under the cryogenic temperature.

SOLUTION: A flat hemming process (figure C) characterized by the feature that the process bonds an aluminum alloy outer panel stock 1 having the wall thickness of 0.8 mm or more to an aluminum alloy inner panel stock 2 having the wall thickness of 1.0 mm or less, and when the flat hemming process is conducted in the condition that a clearance exists between the end portion of the inner panel stock 2 inserted into the hemming portion 16 of the outer panel stock 1 and the internal surface of the hemming portion, the outer panel stock 1 includes Si: 0.4-1.3%, Mg: 0.4-1.2%, and Si/Mg is 1 or more, Mn: 0.15% or less and regulates Cu: 0.1% or less, and proof stress is 110-140 MPa and the outer panel stock is a Si excessive type Al-Mg-Si system aluminum alloy and the outer panel stock after the flat hemming process is granted by 2% stretch and then, proof stress after the artificial aging treatment of 150°C×20 minutes is made 170 MPa or more.



LEGAL STATUS

[Date of request for examination]

22.09.2004

[Date of sending the examiner's decision of rejection]

* NOTICES *

JPO and INPIT are not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

CLAIMS

[Claim(s)]

[Claim 1] Board thickness is 0.8mm. The aluminium alloy outer panel material which it is above Board thickness is 1.0mm. It is the flat hem processing approach joined to the following aluminium alloy inner panel material. It faces carrying out flat hem processing in the condition that a clearance is between the insides of said inner panel material edge inserted in the hemming section of said outer panel material, and said hemming section. Si:0.4-1.3% and Mg:0.4-1.2% are included for said outer panel material. And Si/Mg 1 It is above and they are less than [Mn:0.15%] and Cu:0.1%. It regulates below. It considers as the aluminum-Mg-Si system aluminium alloy of overSi mold which made proof stress the range of 110 -140MPa. And the hem processing approach of the aluminium alloy panel material characterized by setting proof stress after the artificial-aging processing for after [2% stretch grant] 150 **x 20 minutes of the outer panel material after said flat hem processing to 170 or more MPas.

[Claim 2] They are 90-degree bend radii of said aluminium alloy panel material in down flange processing before said flat hem processing 0.5-2.0 The hem processing approach of the aluminium alloy panel material according to claim 1 made into the range.

[Claim 3] Before said flat hem processing, press forming of the aluminium alloy panel material is carried out beforehand, it comes out, and it is the hem processing approach of a certain aluminium alloy panel material according to claim 1 or 2.

[Claim 4] OverSi mold aluminum-Mg-Si system aluminium alloy panel material for outer panel material by which flat hem processing is carried out by the approach of said claim 1 thru/or either of 3.

[Translation done.]

* NOTICES *

JPO and INPIT are not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

DETAILED DESCRIPTION

[Detailed Description of the Invention]

[0001]

[Field of the Invention] This invention relates to the hem processing approach of aluminium alloy panel material, and the aluminium alloy panel material for hem processing (aluminum is only hereafter called aluminum).

[0002]

[Description of the Prior Art] From the former, as the member and the object for components of transport airplanes, such as an automobile, a vessel, or a car, home electronics, construction, and the structure Fabrication nature (only henceforth a moldability) Outstanding AA thru/or outstanding JIS of an aluminum-Mg system It was specified to specification. (specification is satisfied) 5000 A system, AA of an aluminum-Mg-Si system thru/or JIS 6000 system excellent in a moldability or printing hardenability (only henceforth 5000 systems thru/or 6000 systems) aluminum alloy (each aluminium alloy expansion material, such as rolling panel material, an extruded section, and a forging, is named generically) is used.

[0003] In recent years, improvement in the fuel consumption by lightweight-izing of the car body of transport airplanes, such as an automobile, is pursued to the global environment problems by exhaust gas etc. For this reason, instead of the steel materials currently used from the former, application of more nearly lightweight aluminum alloy is increasing to the car body of an automobile especially.

[0004] the inside of this aluminum alloy -- outer panel of the panel structures, such as a hood of an automobile, a fender, a door, a roof, and a trunk lid (shell plate) panel material, such as an inner panel (inner plate), -- thin meat -- and -- as high intensity aluminum alloy panel material -- JIS or it was specified to AA Standard (JIS thru/or AA Standard are satisfied) -- use of aluminum alloy panel (plate) material of 6000 systems of a superfluous Si mold is considered.

[0005] This superfluous Si type of 6000 system aluminum alloy contains Si and Mg as indispensable fundamentally, and is Si/Mg. 1 It is the aluminum-Mg-Si system aluminium alloy which it is above. And the age-hardening of it is carried out with heating at the time of artificial-aging processing of the baking finish processing after shaping etc., and its proof stress improves, and it has the advantage which can secure required reinforcement while it secures a moldability by low proof stress-ization at the time of press forming or bending, since especially this superfluous Si mold 6000 system aluminum alloy has the outstanding age-hardening ability.

[0006] Moreover, a these superfluous Si mold 6000 system aluminum alloy has comparatively few amounts of alloy elements as compared with aluminum alloy of other 5000 systems with many amounts of alloys, such as the amount of Mg, etc. For this reason, it is aluminum alloy dissolution material about the scrap of these 6000 system aluminum alloy. (dissolution raw material) In case it reuses by carrying out, it is easy to obtain the original 6000 system aluminum alloy ingot, and excels also in recycle nature.

[0007] By the outer panel of said automobile panel structure, the edge of an outer panel is bent after the fabrication by the press of a diaphragm process, a trim process, etc. (180 turning up a degree) Hemming processing which performs junction on the edge of the inner panel after fabrication (it is called folding ***** and following hem processing) It is carried out.

[0008] the outline of this hemming processing -- drawing 2 (a) - (d) It is shown. Hemming processing is fundamentally performed by selection of the flat hem process of drawing 2 (c), or the rope hem process of drawing 2 (d) through the down flange process of drawing 2 (a) explained in full detail below, and the PURIHEMU process of drawing 2 (b) as this drawing shows.

[0009] First, the down flange process of drawing 2 (a) is the outer panel 1 after fabrication fixed by dice 3a and holddown 5a. About marginal 1a, it is a right angle (90 **) by punch 4a. It bends to a near include angle.

[0010] Next, the PURIHEMU process of drawing 2 (b) is the outer panel 1 after a down flange process. Similarly, it fixes by dice 3b and holddown 5b, and is the outer panel 1. Marginal 1b is further bent inside to about 135 ** by punch 4b.

[0011] Furthermore, the flat hem process of drawing 2 (c) and the rope hem process of drawing 2 (d) are the inner panel 2 after fabrication, such as a diaphragm process and a trim process. It is the outer panel 1 after a PURIHEMU process about an edge. It holds in the bending section. (insertion) It carries out. and outer panel 1 And inner panel 2 Holddown (not shown) while fixing with Dices 3c and 3d -- outer panel 1 Edges 1c and 1d -- Punch 4c and 4d -- further -- it bends inside to the include angle of 180 **, and a flat hem is formed. Thus, inner panel 2 An edge and outer panel 1 Flat hem section (180 whenever bending section) It contacts, and it is stuck while both are joined in edges.

[0012] It compares with the flat hem process of drawing 2 (c), and the rope hem process of the inside of this and drawing 2 (d) is the hem hemming section (bending section). It has the configuration of a form of a rope which swelled in the shape of radii, and configurations are not Sharp thru/or a flat hem configuration, and appearance nature does not have them, either. [good] Moreover, problems, like junction nature and adhesion are missing few also have the touch area of an outer panel and an inner panel.

[0013] For this reason, in the autoparts which think an appearance and a fine sight as important especially, it is usual to perform the final process of hem processing according to the flat hem process of drawing 2 (c) used as severe bending.

[0014] Setting here, aluminum alloy panel material for said outer panels and inner panels is 1.2mm because of lightweight-izing of panel material. Thinning is increasingly carried out to the following board thickness in recent years. For example, aluminum alloy panel material for outer panels is 0.8mm. The above 0.9-1.2mm Board thickness is in use. Moreover, aluminum alloy panel material for inner panels is 1.0mm. The following 0.8-1.0mm board thickness is in use.

[0015] However, especially in these aluminum alloy panel material by which thinning was carried out, as bending conditions, it becomes severe and flat hem processing becomes difficult, so that the board thickness of the inner panel material inserted in the hemming section of outer panel material becomes thin.

[0016] for this reason, the hemming section A of the flat hem formed in flat hem processing of aluminum alloy panel material by which thinning was carried out **** -- drawing 3 Surface deterioration X as shown in order of extent, minute crack Y, and comparatively big crack Z etc. -- a defect -- being generated -- being easy -- application on components becomes impossible in many cases

[0017] Moreover, it sets to flat hem processing and is drawing 3. Like (it illustrates to drawing 2 (C)) and outer panel material 1 which are shown Hemming section A Inner panel material 2 inserted Edge 2a and the hemming section A Between Insides Aa, it is Clearance t a little inevitably. It is processed in the condition of being. this clearance t it is -- or this clearance t if it becomes large -- outer panel material 1 The hemming section A (bending section) since thickness becomes thin and becomes severe as bending conditions -- crack Z etc. -- it becomes easy to produce a defect. And in the above mentioned aluminum alloy panel material by which thinning was carried out, this inclination becomes remarkable.

[0018] On the other hand, it is said hem section at the flat hem processing process and material side of aluminum alloy plate from the former. (hemming section, bending section) Various techniques of preventing defect generating are also proposed.

[0019] for example, in JP,63-2690,B In flat hem processing of high intensity 186MPa extent aluminum alloy plate Bend radii Rd (shoulder radius of a dice) of the flange corner section formed in outer panel material in the down flange process of said drawing 2 (a) It enlarges. More specifically relation with the board thickness of aluminum alloy plate -- bend radii Rd -- $0.8t-1.8t$ (however, t board thickness of aluminum alloy plate) ***** -- preventing said defect's generating is indicated.

[0020]

[Problem(s) to be Solved by the Invention] However, the inner panel material inserted in the hemming section of outer panel material in flat hem processing in this official report is 1.2mm. It is comparatively as thick as extent and flat hem processing is comparatively easy severely as bending conditions. On the other hand, 0.8-1.0mm When flat hem processing is carried out using the comparatively thin inner panel material of extent, even if it enlarges bend radii Rd etc., a crack arises in the hemming section of a flat hem. This originates also in existence of the clearance between the inner panel material edges and hemming section insides which are inserted in the outer panel material hemming section as it described above.

[0021] For this reason, there is no practical improvement technique of the effective flat hem workability of the above mentioned sheet metal aluminum alloy panel material by the side of a flat hem processing process not much. For this reason, the proof stress of 6000 system aluminum alloy panel material itself was lowered to the ingredient side, and the actual condition has improved flat hem workability.

[0022] However, when reducing the proof stress of 6000 system aluminum alloy panel material too much, the proof stress after paint baking processing (artificial-aging hardening processing) of aluminum alloy panel material becomes low inevitably.

[0023] Especially the temperature of paint baking processing of aluminum alloy panel material is in the inclination

which a low-temperature short time tends to be increasingly formed by a demand and coating improvement of energy saving, and is increasingly low-temperature-ized by them on the low-temperature short-time processing conditions for 150 °C x 20 minutes etc. from the processing for 170 °C x 20 minutes which was conventionally commonsense as for the formation of a low-temperature short time in recent years.

[0024] For this reason, on such paint baking processing conditions formed into a low-temperature short time, when reducing the proof stress of 6000 system aluminum alloy panel material for an improvement of hem workability, the reinforcement of 170 or more MPas required of this seed panel structure application is not obtained.

[0025] Thus, like [the artificial-aging hardenability in the hem workability and the low temperature of 6000 system aluminum alloy panel material which were sheet-metal-ized] an old raise in a moldability, and a technical problem with high-intensity-izing etc., it is the technical technical problem which carries out phase conflict, and it is difficult to make it compatible. For this reason, even if it carries out with the control technique of the crystallization object of 6000 system aluminum alloy panel material, or a sludge proposed variously, and the technique which adds Cu etc. so much from the former, it becomes a quite difficult technical technical problem to attain to coincidence the artificial-aging hardenability in the hem workability and the low temperature of 6000 system aluminum alloy panel material which were sheet-metal-ized.

[0026] This invention is made paying attention to such a situation, and the purpose tends to offer the hem processing approach of aluminum alloy panel material and aluminum alloy panel material for hem processing which are satisfied with coincidence of hem workability and the artificial-aging hardenability in low temperature.

[0027]

[Means for Solving the Problem] In order to attain this purpose, the summary of the hem processing approach (claim 1) of this invention aluminium alloy panel material Board thickness is 0.8mm. The aluminium alloy outer panel material which it is above Board thickness is 1.0mm. It is the flat hem processing approach joined to the following aluminium alloy inner panel material. It faces carrying out flat hem processing in the condition that a clearance is between the insides of said inner panel material edge inserted in the hemming section of said outer panel material, and said hemming section. Si:0.4-1.3% and Mg:0.4-1.2% are included for said outer panel material. And Si/Mg 1 It is above and they are less than [Mn:0.15%] and Cu:0.1%. It regulates below. It is considering as the aluminum-Mg-Si system aluminium alloy of overSi mold which made proof stress the range of 110 -140MPa, and setting proof stress after the artificial-aging processing for after [2% stretch grant] 150 °C x 20 minutes of the outer panel material after said flat hem processing to 170 or more MPas.

[0028] Moreover, aluminium alloy panel material for this invention hem processing (claim 4) A summary is aluminum-Mg-Si system aluminium alloy panel material for outer panel material by which flat hem processing is carried out by the approach of said claim 1 thru/or either of 3.

[0029] In addition, temper processing which mentions a hot rolling plate, a cold rolling plate, and these later with aluminum alloy panel material said by this invention (heat treatment) It is the given plate and names generically, including the plate for shaping.

[0030] Especially for this invention persons, inner panel material is 1.0mm. The 6000 system aluminum alloy panel material sheet-metal-ized below, About flat hem processing in the condition that there is a clearance between the inner panel material edges and hemming section insides which are inserted in the hemming section of outer panel material, hem processing is excellent and on the conditions for the usual 170 °C x 20 minutes and of course Artificial-aging processing of a low-temperature short time for said 150 °C x 20 minutes (paint baking processing) The material conditions from which the reinforcement of 170 or more MPas is obtained also on conditions were examined anew.

[0031] Consequently, if it considers as the aluminum-Mg-Si system aluminium alloy of overSi mold which made proof stress the range of 110 -140MPa, and made the outer panel material by which flat hem processing is carried out the specific component presentation range Especially inner panel material is 1.0mm. It is the 6000 system aluminum alloy panel material sheet-metal-ized below. And even if it was flat hem processing in the condition that there is a clearance between the inner panel material edges and hemming section insides which are inserted in the hemming section of outer panel material, the knowledge of having the effectiveness that can improve hem workability and it is satisfied with coincidence of the artificial-aging hardenability in low temperature was carried out.

[0032] Especially this effectiveness is claim 2. They are 90-degree bend radii of said aluminium alloy panel material in down flange processing before said flat hem processing like a publication 0.5-2.0 It is large when it considers as the range.

[0033] Moreover, since it has such effectiveness, this invention is claim 3. Especially press forming of the 6000 system aluminum alloy plate is beforehand carried out before said flat hem processing, distortion is introduced like a publication and hem processing falls, it is applied to the hem processing approaches for automobile outer panels etc., and is suitable.

[0034]

[Embodiment of the Invention] Hereafter, it explains about the suitable operation gestalt of this invention using a drawing. First, the flat hem processing approach in this invention itself is said drawing 2 (a) - (c). The same is fundamentally said of the conventional hem processing including the flat hem process of having explained, and the conditions of a process and each process.

[0035] However, for considering as the object of flat hem processing by this invention, the board thickness of aluminum alloy outer panel material is 0.8mm as described above. It is above and the board thickness of aluminum alloy inner panel material is 1.0mm. It considers as the following. The board thickness of aluminum alloy outer panel material is thinner than this, and it is comparatively easy for ** to also attain hem workability and the artificial-aging hardenability in low temperature to coincidence not using this invention what has the board thickness of aluminum alloy inner panel material thicker than this.

[0036] In addition, flat hem processing by this invention is 4 of aluminum alloy panel material. Whether all are performed to a perimeter, the side chosen (side edge section) It receives and is chosen suitably, whether it is a line crack corresponding to the design of a member.

[0037] (Down flange process) The down flange process of drawing 2 (a) in hem processing is aluminum alloy outer panel material 1 after extracting as occasion demands and carrying out [process / a process, / trim] fabrication first. It fixes by dice 3a and holddown 5a, and is the outer panel material 1. Marginal 1a is bent to the include angle near a right angle by punch 4a.

[0038] Under the present circumstances, outer panel material 1 90-degree bend radii are 0.5-2.0. Considering as the range is desirable. Outer panel material 1 90-degree bend radii adjust the shoulder radius Rd of dice 3a of drawing 2 (a), and the shoulder radius Rp of punch 4a, and perform them.

[0039] 90-degree bend radii of outer panel material are 0.5. When it is the following, especially inner panel material is 1.0mm. It is the 6000 system aluminum alloy panel material sheet-metal-ized below. and in flat hem processing in the condition that there is a clearance between the inner panel material edges and hemming section insides which are inserted in the hemming section of outer panel material In spite of a proof stress convention of the outer panel material in this invention, it sets at a flat hem processing process, and is said drawing 3. It becomes easy to produce defects, such as a shown crack.

[0040] On the other hand, 90-degree bend radii of outer panel material are 2.0. When exceeding, it becomes close to the rope hem shown in drawing 2 (d), and possibility that a fine sight will be spoiled in the appearance of the hem hemming section becomes large. Moreover, to the outer-diameter line thru/or visible outline on the original design of the hemming section of a flat hem, or the visible outline after actual processing becomes short, possibility that it will be too long conversely and neither configuration precision nor dimensional accuracy will come out also becomes large.

[0041] Next, the PURIHEMU process of drawing 2 (b) is the outer panel material 1 after a down flange process. Similarly, it fixes by dice 3b and holddown 5b, and is the outer panel material 1. Marginal 1b is further bent inside to the include angle of about 135 ** by punch 4b.

[0042] Furthermore, the flat hem process of drawing 2 (c) is the inner panel 2 after fabrication, such as a diaphragm process and a trim process. About an edge, it is the outer panel material 1 after a PURIHEMU process. Hemming section A It inserts.

[0043] under the present circumstances, clearance t produced between inner panel material edge 2a and the hemming section insides Aa which are shown in said drawing 3 as [said] having carried out -- outer panel material 1 The hemming section A in order to make thickness thin and to make bending conditions severe -- crack Z etc. -- a defect is made easy to produce. Therefore, this clearance t The smaller possible one is desirable in respect of flat hem workability. However, this clearance t A hem processing top is difficult for losing completely, and it is also complicated. for this reason -- this invention -- the hemming section A Crack Z etc. -- a certain amount of clearance t in the range which does not produce a defect It approves.

[0044] This clearance t The tolerance in this invention is Clearance t. Flange die length shown in said drawing 3 (perimeter of the hem hemming section A) l Ratio (t/l) Although it changes also with processing conditions when it says, it is 0.6 in general. It is the following. However, by the conventional hem processing, it is this t/l. It is 0.3 in general. Extent was tolerance. Namely, this clearance t that makes bending conditions severe by improvement of flat hem workability in this invention Tolerance can be enlarged and this point is also one of this invention effectiveness.

[0045] And outer panel material 1 And inner panel 2 While fixing by the holddown (not shown) and dice 3c, it is the outer panel 1. It is marginal 1c by punch 4c Further 180 It bends inside to the include angle of whenever, and the flat hem section is formed. Thus, inner panel 2 An edge and outer panel 1 Flat hem section (hemming section) It contacts, and while both are joined in edges, it is stuck mutually.

[0046] Therefore, this invention also has the advantage that achievement of said two effectiveness is possible, without changing a conventional hem processing process and conventional conditions a lot.

[0047] (aluminum alloy panel material) Next, aluminum alloy panel material concerning this invention is explained to a

detail.

[0048] (Proof stress) Let proof stress of aluminum alloy outer panel material first be the range of 110 -140MPa. drawing 1 AA 6016 aluminum alloy in the example boiled and mentioned later (this invention presentation) Proof stress of aluminum alloy panel material (it was made to change variously) Relation with hem workability is shown. drawing 1 inside and a white round mark -- inner panel stock thickness -- 1.0mm and the black dot mark -- inner panel stock thickness -- 0.8mm it is -- it is a case. drawing 1 the hem processing conditions that it can be alike and can set -- inner panel board thickness -- 0.8-1.0mm Clearance t which it is thin and is produced between an inner panel material edge and a hemming section inside Flange die-length l a ratio -- t/l -- 0.5 large -- 90-degree bend radii of a down flange process -- 0.5 It considered as severer flat hem processing.

[0049] drawing 1 since -- the case where proof stress exceeds 140MPa(s) as I understand -- especially -- inner panel material -- 1.0mm It is the 6000 system aluminum alloy panel material sheet-metal-ized below. and, so that inner panel stock thickness is thin on said severe flat hem processing conditions (inner panel stock thickness -- 1.0mm -- the direction in 0.8mm) Hem workability falls and defects, such as a crack, arise in the hemming section of outer panel material. It follows and it turns out on said severe flat hem processing conditions that the criticality of flat hem workability is near proof stress 140MPa by this invention at the target superfluous Si mold 6000 system aluminum alloy panel material.

[0050] On the other hand, the proof stress of aluminum alloy outer panel material is 110 MPa. The low-temperature age-hardening ability made into the purpose is not obtained, the proof stress at the time of the low-temperature aging treatment for after [2% stretch grant] 150 **x 20 minutes is not set to 170 or more MPas, and need reinforcement as the panel structure cannot be filled with the following.

[0051] (Board thickness) Attached to the board thickness of aluminum alloy panel material in this invention, as described above, the board thickness of aluminum alloy outer panel material is 0.8mm. It is above and the board thickness of aluminum alloy inner panel material is 1.0mm. It is aimed at the following. The board thickness of aluminum alloy outer panel material is thinner than this, hem workability is improved according to the effectiveness of board thickness in what has the board thickness of aluminum alloy inner panel material thicker than this, and it is the technical problem of this invention. (hem workability and the artificial-aging hardenability in low temperature are attained to coincidence) Needlessness and **.

[0052] Moreover, the board thickness of aluminum alloy inner panel material is 1.0mm also at the point of lightweight-izing of panel material thru/or the panel structure. It is desirable that it is the following. In addition, as for the one where the board thickness of aluminum alloy inner panel material from the point of flat hem workability is thicker, hem workability of the one where the board thickness of aluminum alloy outer panel material is conversely thinner improves. However, if the board thickness of aluminum alloy inner panel material becomes thick, the meaning of the adoption [itself] of aluminum alloy panel material for lightweight-izing of panel material thru/or the panel structure will be spoiled.

[0053] (aluminum alloy presentation) Next, the chemical entity presentation in this invention outer panel material is explained. Especially the outer panel aluminum alloy of this invention makes many properties, such as the press-forming nature and corrosion resistance which are excellent in said hem workability or low-temperature age-hardening ability, and are further demanded considering proof stress as range of 110 -140MPa as the panel structure of transport airplanes, such as an automobile, etc. as a superfluous Si mold 6000 system aluminum alloy, and weldability, have. (it is satisfied) There is need. therefore, the content of each elements, such as Si in this invention aluminum alloy panel material, and Mg, -- AA thru/or JIS specification -- a convention -- or while being contained, it is specified in the desirable range from a viewpoint of said property exertion within the limits of it. Below, the desirable range of each element and meaning are explained.

[0054] in addition, Cr(s), Zr, Ti and B other than the inside of an alloy element, and Si, Mg, Cu and Mn, and Fe, Zn, nickel and V etc. -- other alloy elements are impurity elements fundamentally. However, the case where not only a high grade aluminum metal but a 6000 system alloy, other aluminum alloy scrap material, a low purity aluminum metal, etc. are used as dissolution material is included as dissolution material from a viewpoint of recycle of said 6000 system alloy. In such a case, an alloy element besides these will be contained inevitably. Therefore, an alloy element besides these is JIS in the range which does not check said improvement effectiveness in many properties made into the purpose in this invention. Or it permits containing within the specification of AA.

[0055] Mg: 0.4-1.2%.

Mg is Mg/Si in Si at the time of solid solution strengthening and artificial-aging processing of paint baking processing etc. Compound phases, such as a cluster, are formed, age-hardening ability is demonstrated, and it is an indispensable element for obtaining the need reinforcement of 170 or more MPas as panel material thru/or the panel structure.

[0056] Less than 0.4% of Mg (it is the same mass % and the following) In content, since absolute magnitude runs short, said compound phase cannot be formed at the time of artificial-aging processing, and age-hardening ability cannot be

demonstrated. For this reason, as panel material thru/or the panel structure, the need reinforcement of 170 or more MPas is not obtained.

[0057] if Mg contains on the other hand exceeding 1.2% -- press-forming nature and bending workability (hem workability) etc. -- a moldability is checked remarkably. Therefore, the content of Mg is 0.4 - 1.2% of range, and is Si/Mg. 1.0 Considering as an amount which becomes the above is desirable.

[0058] Si: 0.4-1.3%.

Si is [Mg] Mg/Si in Si at the time of solid solution strengthening and artificial-aging processing of paint baking processing etc. Compound phases, such as a cluster, are formed, age-hardening ability is demonstrated, and it is an indispensable element for obtaining the need reinforcement of 170 or more MPas as panel material thru/or the panel structure. Therefore, it is the maximum important element for making many properties, such as the press-forming nature and hem workability which are in an overthis invention Si mold 6000 system aluminum alloy, and are further required of each application, corrosion resistance, and weldability, have.

[0059] Moreover, it is Si/Mg also in order to demonstrate the outstanding low-temperature age-hardening ability of 170 or more MPas for the proof stress at the time of the low-temperature aging treatment for after [2% stretch grant] 150 **x 20 minutes. 1.0 It considers as the above and considers as the superfluous Si mold 6000 system aluminum alloy presentation which made Si contain superfluously to Mg.

[0060] The amount of Si cannot have many properties, such as said age-hardening ability, press-forming nature further required of each application, hem workability, corrosion resistance, and weldability, at less than 0.4%.

[0061] On the other hand, if Si contains exceeding 1.3%, hem workability and bending workability will be checked especially remarkably. Furthermore, weldability is checked remarkably. Therefore, as for Si, it is desirable to consider as 0.4 - 1.3% of range.

[0062] In addition, in especially outer panel material, since hem workability is thought as important, as for Si content, it is desirable that they are 0.4 - 1.1% and the more lower range.

[0063] Cu: 0.1% The following and Cu are Mg/Si into the crystal grain of aluminum alloy organization at usual at the time of artificial-aging processing of paint baking processing etc. The effectiveness of promoting compound phases, such as a cluster, and Cu which dissolved are effective in raising a moldability. However, especially inner panel material is 1.0mm. In flat hem processing in the condition that there is a clearance between the inner panel material edges and hemming section insides which are the sheet metal-sized 6000 system aluminum alloy panel material, and are moreover insert in below at the hemming section of outer panel material, if Cu is contain exceeding 0.1%, hem workability will fall and defects, such as a crack, will arise in the hemming section of outer panel material. Moreover, content of Cu degrades remarkably stress-corrosion-cracking-proof nature, the yarn-proof rust nature of the corrosion resistance after paint, and weldability. For this reason, in the case of the panel material applications for automobile outer panels etc., it considers as 0.1% or less of the smallest possible amount especially.

[0064] Mn: In less than [0.15%] and Mn, it is a particulate material at the time of homogenization heat treatment. (dispersed phase) It generates, the grain boundary migration after recrystallization is barred to these particulate materials, and it is effective in making the crystal grain of aluminum alloy organization make it detailed. However, 0.15% Especially by the content to exceed, inner panel material is 1.0mm. In flat hem processing in the condition that there is a clearance between the inner panel material edges and hemming section insides which are the sheet-metal-sized 6000 system aluminum alloy panel material, and are moreover inserted in below at the hemming section of outer panel material, hem workability falls and defects, such as a crack, arise in the hemming section of outer panel material. Therefore, the content of Mn is 0.15%. It regulates below.

[0065] Cr, Zr.

It is a particulate material like [the transition element of these Cr and Zr] Mn at the time of homogenization heat treatment. (dispersed phase) It generates and is effective in the ability to obtain detailed crystal grain. However, Cr and Zr are also 0.15%. Especially by the content to exceed, inner panel material is 1.0mm. In flat hem processing in the condition that there is a clearance between the inner panel material edges and hemming section insides which are the sheet-metal-sized 6000 system aluminum alloy panel material, and are moreover insert in below at the hemming section of outer panel material, hem workability falls and defects, such as a crack, arise in the hemming section of outer panel material. Therefore, the content of Cr and Zr is also 0.15%. Regulating below is desirable.

[0066] Ti and B.

Ti and B If contained Ti:0.1% respectively exceeding B:300 ppm, a big and rough crystallization object will be formed and a moldability will be reduced. however, Ti and B **** -- by content of a minute amount, crystal grain of an ingot is made detailed and it is effective in raising press-forming nature. Therefore, Ti:0.1% The content to B:300 ppm or less is permitted hereafter.

[0067] Fe.

Fe which mixes from dissolution material and is contained as an impurity generates crystallization objects, such as

aluminum₇Cu₂Fe, aluminum₁₂(Fe, Mn)₃Cu₂, and aluminum (Fe, Mn)₆. These crystallization objects degrade remarkably moldabilities, such as fracture toughness and a fatigue property, and also hem workability. Especially, the content of Fe is 0.50%. Since these properties will deteriorate notably if it exceeds, it is the content (permissible dose) of Fe preferably. 0.50% Considering as the following smallest possible amounts is desirable.

[0068] Zn.

If Zn is contained exceeding 0.1%, corrosion resistance will fall notably. Therefore, as for the content of Zn, it is desirable to consider as 0.1% or less of the smallest possible amount preferably.

[0069] Moreover, the same quality of the material as the above-mentioned outer panel material is sufficient as the quality of the material of the inner panel material of this invention, and they may differ. From a viewpoint of the formation of a uni-alloy of planning convenience of supply or recycle for outer panel material and inner panel material as an aluminum alloy of the same quality of the material, the 6000 system aluminum alloy of the same superfluous Si mold as said outer panel material is desirable. However, it is not necessary to make the inner panel material as the panel structure of transport airplanes, such as an automobile, etc. have many severe demand properties like the above-mentioned outer panel material in addition to press-forming nature. For this reason, even if not the same as said outer panel material, they are AA thru/or JIS. 3000 A system and aluminum-Mg System 5000 system and 6000 aluminum alloy excellent in press-forming nature, such as a system, can use it suitably.

[0070] (The manufacture approach) The superfluous Si mold 6000 system aluminum alloy outer panel material and inner panel material in this invention which consist of the above presentation can be manufactured with a conventional method. however, each process by the conventional method from the need of making outer panel material having many demand properties as [said] carried out -- also setting -- each -- there are desirable manufacture conditions and it explains below including this point.

[0071] The usual dissolution casting, such as the continuous casting rolling-out method and a semi-continuous casting method (direct chill casting process), is chosen suitably, and the superfluous aluminum alloy molten metal by which dissolution adjustment was carried out at this invention component specification within the limits is cast in the dissolution and a casting.

[0072] Subsequently, hot rolling after performing homogenization heat treatment to this aluminum alloy ingot - Cold rolling (as occasion demands, it hot-rolls - while giving intermediate annealing of a batch type or continuous system etc. between cold-rolling between cold-rolling) It carries out and the configuration of panel material, such as a coiled form and tabular, is processed.

[0073] aluminum alloy after processing is solution-izing and hardening processing (T four processing) indispensable first as temper processing. It is carried out. Solution-izing and hardening processing are Mg/Si by artificial-aging processing of next paint baking hardening processing etc. A cluster and beta" It is an important process in order to deposit compound phases, such as a phase, in a grain enough. As for the solution treatment conditions for taking out this effectiveness, it is desirable to carry out in the temperature requirement of 500 - 550 **.

[0074] However, when it is the panel material by which especially hem workability is thought as important, solution treatment conditions are more desirable than that of 500 - 530 ** a low temperature side.

[0075] A cooling rate is 300 **/in the case of hardening after solution treatment. Considering as quenching more than a part is desirable. A cooling rate is 300 **/. When under a part is late, the reinforcement after hardening becomes low, age-hardening ability runs short, and high proof stress of 170 or more MPas cannot be secured by artificial-aging processing of next paint baking hardening processing etc.

[0076] Moreover, at the time of quenching after solution-izing, on a grain boundary, Si, MgSi, etc. become easy to deposit, the origin of the crack at the time of press forming or hem processing is easy to come, and these moldabilities fall. Although air cooling, such as a fan, may be used for hardening processing in order to secure this cooling rate, it is desirable to carry out by choosing from water-cooled means, such as Myst, a spray, and immersion.

[0077] Si which causes room temperature aging control after solution-ized hardening processing - A hole and Si/In order to control generation of the hole cluster itself, it is desirable to carry out reserve aging treatment. That is, the thing of 1 - 24 hours to do for need time amount maintenance is desirable to the temperature requirement of 50 - 100 **. Moreover, the cooling rate after reserve aging treatment is 1 **/hr. It is desirable that it is the following.

[0078] after making high hardening termination temperature after solution treatment with 50 - 100 ** as this reserve aging treatment -- immediately -- reheating -- or it carries out by holding as it is. Or after hardening processing to after [solution treatment] ordinary temperature, it carries out by reheating to 50 - 100 ** immediately.

[0079] Moreover, in continuation solution-ized hardening processing, hardening processing is ended in the temperature requirement of said reserve aging, and it carries out to it by rolling round in a coil at an elevated temperature as it is. In addition, before rolling round in a coil, it may reheat, or you may keep it warm after rolling up. Moreover, after hardening processing to ordinary temperature, it reheats to said temperature requirement and you may carry out rolling round at an elevated temperature etc.

[0080]

[Example] Next, the example of this invention is explained.

(Example 1) First, as a superfluous Si mold 6000 system aluminum alloy for outer panel material, solution treatment conditions were changed for aluminum alloy plate of an AA 6016 aluminum alloy specification presentation, and said reserve aging treatment was performed alternatively, and proof stress was variously changed with the thing of this invention within the limits of 110 -140MPa, and the thing which separated from this range, and was created. this AA 6016 aluminum alloy presentation -- Table 1 No. -- 1 and 2 It is shown. The superfluous Si mold [of an alloy presentation] thru/or superfluous Mg mold 6000 system aluminum alloy plate which separated from this invention range for the comparison was also prepared. these -- aluminum an alloy presentation -- Table 1 No. -- 3, 4, and 5 It is shown. Moreover, it is Table 2 about the board thickness of aluminum alloy plate of the example of invention, and the example of a comparison, and the proof stress after temper processing. It is shown.

[0081] Creation of aluminum alloy plate was taken as the following conditions. 50mm ingot of aluminum alloy -- a direct chill casting process -- after an ingot and 550 **x4 homogenization heat treatment of time amount -- giving -- the temperature below 480 ** -- 5mm in thickness up to -- it hot-rolled. this hot rolling plate -- the programming rate of 40 degrees C / hr the conditions for 500 **x 30 seconds -- annealing processing -- carrying out -- after that, thickness 0.8, and 1.0mm up to -- it cold-rolled. After processing this cold-rolled plate by changing solution treatment conditions in the range of 500 - 550 ** in a heat treating furnace further, T-four temper processing in which hardening by water cooling thru/or air cooling was performed immediately was performed.

[0082] The cooling rate in the case of said hardening is 50-600 **/. It adjusts in the range of a part and is hardening termination temperature (hardening temperature). It considers as 80 degrees C in common, and is 2 at this temperature after hardening. Reserve aging which carries out time amount maintenance (cooling rate 1 ** [after maintenance]/hr following) It carried out.

[0083] Strip-of-paper-like sample offering plate for the hem processing trial from these aluminum alloy plates (blank) Two or more sheets were started, in advance of hem processing, fabrication, such as a diaphragm of the outer panel of an automobile door and a trim process, was first simulated to this blank, and 5% of distortion was given beforehand. And flat hem machining allowance of a blank (it bends from the edge bent inside the outer panel blank after hem processing, and is the distance to the edge of the section) It was referred to as 12mm and the following hem processings were performed.

[0084] First, blank which gave distortion beforehand according to the down flange process shown in said drawing 2 (a) (outer panel) The edge was bent until it became the include angle of 90 degrees. Under the present circumstances, they are 90-degree bend radii of aluminum alloy panel material 0.5-1.0 It changed. Adjustment of 90-degree bend radii was performed in the shoulder radius Rd of dice 3a. It is Table 2 about 90-degree bend radii of these aluminum alloy panel material. It is shown.

[0085] next, the PURIHEMU process shown in drawing 2 (b) -- the edge of a blank -- further -- it bent inside to the include angle of 135 **.

[0086] then -- the same -- from said aluminum alloy plate -- starting -- blank as an inner panel (the same panel material as the AA 6016 aluminum alloy which is outer panel material --) About the edge of 0.8-1.0mm of board thickness, it is said blank. (outer panel) Clearance t which inserts in the bending section and is produced between an inner panel material edge and a hemming section inside It prepared and the flat hem was prepared according to the flat hem process further shown in drawing 2 (c). The board thickness and said clearance t between these inner panels Table 2 It is shown. however, clearance t Flange die-length l a ratio -- t/l It is shown.

[0087] And visual observation of the surface states, such as generating of the surface deterioration of the hemming section of a flat hem, a minute crack, and a big crack, was carried out. 3; which a crack including a minute thing does not have although evaluation also has neither 1; surface deterioration nor a minute crack and fitness and 2; surface deterioration have occurred -- a minute crack -- generating and 4; -- a big crack -- generating and 5; -- a big crack -- 5 of plurality thru/or a large number generating ** The phase was evaluated. As this evaluation, hem workability is good. (use is possible) Being judged is 1-2. It is to a phase and is 3. Hem workability is inferior in beyond a phase. (use is impossible) It is judged.

[0088] Furthermore, proof stress after carrying out artificial-aging hardening processing of said aluminum alloy plate after manufacture in a low-temperature short time for after [2% stretch grant] 150 **x 20 minutes (BH proof stress, BEKU hard proof stress) It measured and low-temperature aging treatment ability was investigated. These results are combined with said flat hem workability, and are shown in Table 2.

[0089] Table 2 since -- a clear passage by this invention proof stress within the limits of 110 -140MPa and outer panel material of overthis invention Si mold 6000 system aluminum alloy presentation within the limits (No. of Table 1 aluminum alloy of 1 and 2) Example No.of invention1-6 used Inner panel board thickness is 0.8mm. Clearance t which it is thin and is produced between an inner panel material edge and a hemming section inside It is large and 90-degree

bend radii of a down flange process are 0.5. Even if it is severe hem processing A certain thing understands BH proof stress after passing, and MU workability's being excellent and carrying out artificial-aging hardening processing in a low-temperature short time which is 150 **x 20 minutes for 170 or more MPas.

[0090] however, outer panel material of overthis invention Si mold 6000 system aluminum alloy presentation within the limits (No. of Table 1 aluminum alloy of 1 and 2) it is -- even if -- Proof stress exceeds this invention upper limit of 140MPa(s), and, for the high example 7 of a comparison, inner panel board thickness is 0.8mm. Clearance t which it is thin and is produced between an inner panel material edge and a hemming section inside It is large and 90-degree bend radii of a down flange process are 0.5. The crack has arisen in severe hem processing. Moreover, example 8 of a comparison especially with as high proof stress as 152MPa(s) It is 1.0mm about inner panel board thickness. Clearance t which it is thick and is produced between an inner panel material edge and a hemming section inside It is small and they are 90-degree bend radii of a down flange process 1.0 It enlarged, and even if it eases hem processing conditions, the crack has arisen.

[0091] furthermore, outer panel material of overthis invention Si mold 6000 system aluminum alloy presentation within the limits (No. of Table 1 aluminum alloy of 1 and 2) it is -- even if -- although the crack has not produced the example 9 of a comparison with proof stress lower than this invention minimum of 110MPa(s), and 10 in hem processing, BH proof stress after carrying out artificial-aging hardening processing in a low-temperature short time for 150 **x 20 minutes does not fill 170MPa(s).

[0092] moreover, even if proof stress is this invention within the limits, it separates from the overthis invention Si mold 6000 system aluminum alloy presentation range (No. of Table 1 -- 3 and 4 --) 5 aluminum alloy The examples 11, 12, and 13 of a comparison using outer panel material It is 1.0mm about inner panel board thickness. Clearance t which it is thick and is produced between an inner panel material edge and a hemming section inside It is small and they are 90-degree bend radii of a down flange process 1.0 It enlarged, and even if it eases hem processing conditions, the crack has arisen.

[0093] The above result shows the criticality-meaning from the overthis invention Si mold 6000 system aluminum alloy presentation and the flat hem workability of proof stress in this invention, and low-temperature aging treatment ability.

[0094]

[Table 1]

番号	Al合金板の化学成分 (質量%, 但しB はppm、残部Al)										備考
	Si	Fe	Cu	Mn	Mg	Cr	Zn	Zr	Ti	B	
1	1.1	0.25	0.05	0.05	0.5	-	-	-	0.01	30	6016
2	0.85	0.25	0.05	0.05	0.6	-	-	-	0.01	30	6N01
3	0.65	0.25	0.15	0.05	1.0	0.15	-	-	0.01	30	6061
4	0.85	0.25	0.05	0.5	0.6	-	-	-	0.01	30	6N01
5	1.1	0.25	0.20	0.05	0.5	-	-	-	0.01	30	6016

[0095]

[Table 2]

適用	番号	合金番号	アウタ材		へム加工			へム縁曲部	特性
			耐力 MPa	板厚 mm	90° 曲 げ半径	イン ナ板 厚mm	インナ 先端隙 間t/l	表面状態 (割れの 有無)	人工時効 H耐力 (MPa)
発 明 例	1	1	112	1.0	0.5	0.8	0.5	1	172
	2	1	124	1.0	0.5	0.8	0.5	1	180
	3	1	138	1.0	0.5	0.8	0.5	1	183
	4	2	110	1.0	0.5	0.8	0.5	1	173
	5	2	125	1.0	0.5	0.8	0.5	1	178
	6	2	136	1.0	0.5	0.8	0.5	1	181
比 較 例	7	1	143	1.0	0.5	0.8	0.5	3	188
	8	1	152	1.0	1.0	1.0	0.2	5	190
	9	1	105	1.0	0.5	0.8	0.5	1	160
	10	2	107	1.0	0.5	0.8	0.5	1	162
	11	3	129	1.0	1.0	1.0	0.2	3	172
	12	4	134	1.0	1.0	1.0	0.2	4	175
	13	5	133	1.0	1.0	1.0	0.2	4	175

[0096]

[Effect of the Invention] According to this invention, the hem processing approach of aluminum alloy panel material and aluminum alloy panel material for hem processing which are satisfied with coincidence of hem workability and the artificial-aging hardenability in low temperature can be offered. Therefore, it is the point that expansion of the application to transport airplanes, such as an automobile of aluminum alloy, etc. can be aimed at, and has great industrial value.

[Translation done.]

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2003-039124

(43)Date of publication of application : 12.02.2003

(51)Int.Cl. B21D 39/02
 B21D 19/08
 C22C 21/02
 C22C 21/06
 C22F 1/05
 // C22F 1/00

(21)Application number : 2001-224631

(71)Applicant : KOBE STEEL LTD


(22)Date of filing : 25.07.2001

(72)Inventor : NODA KENJI

(54) HEMMING PROCESS OF ALUMINUM ALLOY PANEL STOCK AND ALUMINUM ALLOY PANEL STOCK**(57)Abstract:**

PROBLEM TO BE SOLVED: To provide a hemming process of an aluminum alloy panel stock and an aluminum alloy panel stock for hemming process capable of simultaneously satisfying hemming workability and artificial aging hardenability under the cryogenic temperature.

SOLUTION: A flat hemming process (figure C) characterized by the feature that the process bonds an aluminum alloy outer panel stock 1 having the wall thickness of 0.8 mm or more to an aluminum alloy inner panel stock 2 having the wall thickness of 1.0 mm or less, and when the flat hemming process is conducted in the condition that a clearance exists between the end portion of the inner panel stock 2 inserted into the hemming portion 16 of the outer panel stock 1 and the internal surface of the hemming portion, the outer panel stock 1 includes Si: 0.4-1.3%, Mg: 0.4-1.2%, and Si/Mg is 1 or more, Mn: 0.15% or less and regulates Cu: 0.1% or less, and proof stress is 110-140 MPa and the outer panel stock is a Si excessive type Al-Mg-Si system aluminum alloy and the outer panel stock after the flat hemming process is granted by 2% stretch and then, proof stress after the artificial aging treatment of 150° C × 20 minutes is made 170 MPa or more.

**LEGAL STATUS**

[Date of request for examination]

22.09.2004

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

(19) 日本国特許庁 (J P)

(12) 公開特許公報 (A)

(11) 特許出願公開番号
特開2003-39124
(P2003-39124A)

(43) 公開日 平成15年2月12日 (2003.2.12)

(51) IntCl.	識別記号	FI	テームコード* (参考)
B 2 1 D 39/02 19/08	Z A B	B 2 1 D 39/02 19/08	Z A B E C F
C 2 2 C 21/02 21/06		C 2 2 C 21/02 21/06	
審査請求 未請求 請求項の数 4 O L (全 10 頁) 最終頁に続く			

(21) 出願番号 特願2001-224631(P2001-224631)

(22) 出願日 平成13年7月25日 (2001.7.25)

(71) 出願人 000001199

株式会社神戸製鋼所

兵庫県神戸市中央区脇浜町二丁目10番26号

(72) 発明者 野田 研二

栃木県真岡市鬼怒ヶ丘15番地 株式会社神

戸製鋼所真岡製造所内

(74) 代理人 100089196


弁理士 梶 良之 (外1名)

(54) 【発明の名称】 アルミニウム合金パネル材のヘム加工方法およびアルミニウム合金パネル材

(57) 【要約】 (修正有)

【課題】 ヘム加工性と低温での人工時効硬化能とを同時に満足する、Al合金パネル材のヘム加工方法およびヘム加工用Al合金パネル材を提供する。

【解決手段】 板厚が0.8mm 以上であるアルミニウム合金アウトパネル材1を、板厚が1.0mm 以下のアルミニウム合金インナパネル材2に接合するフラットヘム加工方法C図であって、アウトパネル材1の縁曲げ部16に挿入されるインナパネル材2端部と縁曲げ部の内面との間に隙間がある状態でフラットヘム加工するに際し、アウトパネル材1を、Si:0.4~1.3%、Mg:0.4~1.2%を含み、かつSi/Mgが1 以上であり、Mn:0.15%以下、Cu:0.1%以下に規制し、耐力を110 ~140MPaの範囲としたSi過剰型のAl-Mg-Si系アルミニウム合金とし、かつフラットヘム加工後のアウトパネル材の2%ストレッチ付与後150℃×20分の人工時効処理後の耐力を170MPa以上としたことである。



【特許請求の範囲】

【請求項1】 板厚が0.8mm以上であるアルミニウム合金アウトパネル材を、板厚が1.0mm以下のアルミニウム合金インナパネル材に接合するフラットヘム加工方法であって、前記アウトパネル材の縁曲げ部に挿入される前記インナパネル材端部と前記縁曲げ部の内面との間に隙間がある状態でフラットヘム加工するに際し、前記アウトパネル材を、Si:0.4~1.3%、Mg:0.4~1.2%を含み、かつSi/Mgが1以上であり、Mn:0.15%以下、Cu:0.1%以下に規制し、耐力を110~140MPaの範囲としたSi過剰型のAl-Mg-Si系アルミニウム合金とし、かつ前記フラットヘム加工後のアウトパネル材の2%ストレッチ付与後150℃×20分の人工時効処理後の耐力を170MPa以上とすることを特徴とするアルミニウム合金パネル材のヘム加工方法。

【請求項2】 前記フラットヘム加工に先立つダウンフランジ加工における前記アルミニウム合金パネル材の90°曲げ半径を0.5~2.0の範囲とする請求項1に記載のアルミニウム合金パネル材のヘム加工方法。

【請求項3】 前記フラットヘム加工の前にアルミニウム合金パネル材が予めプレス成形されるである請求項1または2に記載のアルミニウム合金パネル材のヘム加工方法。

【請求項4】 前記請求項1乃至3のいずれかの方法でフラットヘム加工されるアウトパネル材用のSi過剰型Al-Mg-Si系アルミニウム合金パネル材。

【発明の詳細な説明】

【0001】

【発明の属する技術分野】本発明は、アルミニウム合金パネル材のヘム加工方法およびヘム加工用アルミニウム合金パネル材（以下、アルミニウムを単にAlと言う）に関するものである。

【0002】

【従来の技術】従来から、自動車、船舶あるいは車両などの輸送機、家電製品、建築、構造物の部材や部品用として、成形加工性（以下、単に成形性と言う）に優れたAl-Mg系のAA乃至JIS規格に規定された（規格を満足する）5000系や、成形性や焼付硬化性に優れたAl-Mg-Si系のAA乃至JIS 6000系（以下、単に5000系乃至6000系と言う）のAl合金材（圧延パネル材、押出形材、鍛造材などの各アルミニウム合金展伸材を総称する）が使用されている。

【0003】近年、排気ガス等による地球環境問題に対して、自動車などの輸送機の車体の軽量化による燃費の向上が追求されている。このため、特に、自動車の車体に対し、従来から使用されている鋼材に代わって、より軽量のAl合金材の適用が増加しつつある。

【0004】このAl合金材の中でも、自動車のフード、フェンダー、ドア、ルーフ、トランクリッドなどのパネル構造体の、アウトパネル（外板）やインナパネル（内

板）等のパネル材には、薄肉でかつ高強度Al合金パネル材として、JIS乃至AA規格に規定された（JIS乃至AA規格を満足する）、過剰Si型の6000系のAl合金パネル（板）材の使用が検討されている。

【0005】この過剰Si型の6000系Al合金は、基本的には、Si、Mgを必須として含み、かつSi/Mgが1以上である、Al-Mg-Si系アルミニウム合金である。そして、この過剰Si型6000系Al合金は、特に優れた時効硬化能を有しているため、プレス成形や曲げ加工時には低耐力化により成形性を確保するとともに、成形後の焼付塗装処理などの人工時効処理時の加熱により時効硬化して耐力が向上し、必要な強度を確保できる利点がある。

【0006】また、これら過剰Si型6000系Al合金材は、Mg量などの合金量が多い、他の5000系のAl合金などに比べて、合金元素量が比較的少ない。このため、これら6000系Al合金材のスクラップを、Al合金溶解材（溶解原料）として再利用する際に、元の6000系Al合金鋳塊が得やすく、リサイクル性にも優れている。

【0007】前記自動車パネル構造体のアウトパネルでは、絞り工程やトリム工程等のプレスなどによる成形加工後に、アウトパネルの縁を折り曲げて（180度折り返して）、成形加工後のインナパネルの縁との接合を行う、ヘミング加工（はぜ折り加工、以下ヘム加工と言う）が行われる。

【0008】このヘミング加工の概要を図2(a)~(d)に示す。同図から分かる通り、ヘミング加工は、以下に詳述する、図2(a)のダウンフランジ工程、図2(b)のプリヘム工程を経て、図2(c)のフラットヘム工程か図2(d)のロープヘム工程の選択により基本的に行われる。

【0009】まず、図2(a)のダウンフランジ工程は、ダイス3aと板押さえ5aにより固定した、成形加工後のアウトパネル1の縁1aを、ポンチ4aにより、直角(90°)に近い角度まで折り曲げる。

【0010】次に、図2(b)のプリヘム工程は、ダウンフランジ工程後のアウトパネル1を、同じく、ダイス3bと板押さえ5bにより固定し、アウトパネル1の縁1bを、ポンチ4bにより、更に約135°まで内側に折り曲げる。

【0011】更に、図2(c)のフラットヘム工程や図2(d)のロープヘム工程は、絞り工程やトリム工程等の成形加工後のインナパネル2の縁をプリヘム工程後のアウトパネル1の折り曲げ部に収容（挿入）する。そして、アウトパネル1およびインナパネル2とを、板押さえ（図示せず）とダイス3c、3dにより固定するとともに、アウトパネル1の縁1c、1dを、ポンチ4c、4dにより、更に180°の角度まで内側に折り曲げフラットヘムを形成する。このようにして、インナパネル2の縁と、アウトパネル1のフラットヘム部（180度折り曲げ部）とが接触して、両者が端部同士において接合されるとともに密着される。

【0012】この内、図2(d)のロープヘム工程は、図2

(c)のフラットヘム工程に比較して、ヘム縁曲部(折り曲げ部)の形状が、円弧状に膨らんだ、ローブ状の形状を有しており、シャープ乃至フラットなヘム形状ではなく、外観性も良くない。また、アウタパネルとインナパネルとの接触面積が少なく接合性や密着性に欠ける等の問題もある。

【0013】このため、特に、外観や美観を重視する自動車部品などにおいては、ヘム加工の最終工程を、厳しい曲げ加工となる、図2(c)のフラットヘム工程により行うことが通常となっている。

【0014】ここにおいて、前記アウタパネルとインナパネル用のAl合金パネル材は、パネル材の軽量化のために、1.2mm以下の板厚に近年益々薄肉化されている。例えば、アウタパネル用のAl合金パネル材は0.8mm以上の、0.9~1.2mmの板厚が主流である。また、インナパネル用のAl合金パネル材は1.0mm以下の、0.8~1.0mmの板厚が主流である。

【0015】しかし、これら薄肉化されたAl合金パネル材では、特にアウタパネル材の縁曲部に挿入されるインナパネル材の板厚が薄くなるほど、曲げ条件としては厳しくなり、フラットヘム加工が難しくなる。

【0016】このため、薄肉化されたAl合金パネル材のフラットヘム加工において、形成されるフラットヘムの縁曲部Aには、図3に程度順に示すような、肌荒れX、微小な割れY、比較的大きな割れZ等の不良が生じ易くなり、部品への適用ができなくなることが多い。

【0017】また、フラットヘム加工においては、図3に示すように(図2(c)にも図示)、アウタパネル材1の縁曲部Aに挿入されるインナパネル材2の端部2aと、縁曲部Aの内面Aaとの間には、必然的に若干隙間Iがある状態で加工される。この隙間Iがある乃至この隙間Iが大きくなると、アウタパネル材1の縁曲部A(曲げ部)の厚みが薄くなり、曲げ条件としては厳しくなるため、割れZ等の不良が生じ易くなる。そして、前記した薄肉化されたAl合金パネル材では、この傾向が顕著となる。

【0018】これに対し、従来から、フラットヘム加工工程側や、Al合金板の素材側で、前記ヘム部(縁曲部、折り曲げ部)の不良発生を防止する技術も種々提案されている。

【0019】例えば、特公昭63-2690号公報などでは、186MPa程度の高強度なAl合金板のフラットヘム加工において、前記図2(a)のダウンフランジ工程において、アウタパネル材に形成されるフランジコーナー部の曲げ半径Rd(ダイスの肩半径)を大きくし、より具体的には、Al合金板の板厚との関係で、曲げ半径Rdを0.8t~1.8t(但しtはAl合金板の板厚)として、前記不良の発生を防止することが開示されている。

【0020】

【発明が解決しようとする課題】しかし、同公報では、フラットヘム加工において、アウタパネル材の縁曲部に

挿入されるインナパネル材は1.2mm程度と比較的厚く、曲げ条件としては厳しくなく、フラットヘム加工が比較的容易である。これに対し、0.8~1.0mm程度の比較的薄いインナパネル材を用いてフラットヘム加工した場合、曲げ半径Rdなどを大きくしても、フラットヘムの縁曲部に割れが生じる。これは、前記した通り、アウタパネル材縁曲部に挿入されるインナパネル材端部と縁曲部内面との間の隙間の存在にも起因している。

【0021】このため、フラットヘム加工工程側における、前記した薄板Al合金パネル材の有効なフラットヘム加工性の実質的な改善技術はあまり無い。このため、材料側において、6000系Al合金パネル材の耐力自体を下げ、フラットヘム加工性を改善していたのが実情である。

【0022】しかし、6000系Al合金パネル材の耐力を低下させすぎた場合、Al合金パネル材の塗装焼き付け処理(人工時効硬化処理)後の耐力が必然的に低くなる。

【0023】特に、近年、Al合金パネル材の塗装焼き付け処理の温度は、省エネルギー化の要求と塗料改善とによって、益々低温短時間化される傾向にあり、従来低温短時間化の常識的であった、170℃×20分の処理から、150℃×20分の低温短時間処理条件などに、益々低温化する傾向にある。

【0024】このため、このような低温短時間化された塗装焼き付け処理条件では、ヘム加工性の改善のために、6000系Al合金パネル材の耐力を低下させた場合、この種パネル構造体用途に要求される170MPa以上の強度が得られない。

【0025】このように、薄板化された6000系Al合金パネル材のヘム加工性と低温での人工時効硬化能とは、これまでの高成形性化と高強度化などとの課題と同様に、相矛盾する技術課題であって、両立させることは難しい。このため、従来から種々提案されている6000系Al合金パネル材の晶出物や析出物の制御技術や、Cuなどを多量に添加する技術をもってしても、薄板化された6000系Al合金パネル材のヘム加工性と低温での人工時効硬化能とを同時に達成することはかなり難しい技術課題となる。

【0026】本発明はこの様な事情に着目してなされたものであって、その目的は、ヘム加工性と低温での人工時効硬化能とを同時に満足する、Al合金パネル材のヘム加工方法およびヘム加工用Al合金パネル材を提供しようとするものである。

【0027】

【課題を解決するための手段】この目的を達成するために、本発明アルミニウム合金パネル材のヘム加工方法(請求項1)の要旨は、板厚が0.8mm以上であるアルミニウム合金アウタパネル材を、板厚が1.0mm以下のアルミニウム合金インナパネル材に接合するフラットヘム加工方法であって、前記アウタパネル材の縁曲げ部に挿入さ

れる前記インナパネル材端部と前記縁曲げ部の内面との間に隙間がある状態でフラットヘム加工するに際し、前記アウトパネル材を、Si:0.4~1.3%、Mg:0.4~1.2%を含み、かつSi/Mgが1以上であり、Mn:0.15%以下、Cu:0.1%以下に規制し、耐力を110~140MPaの範囲としたSi過剰型のAl-Mg-Si系アルミニウム合金とし、かつ前記フラットヘム加工後のアウトパネル材の2%ストレッチ付与後150℃×20分の人工時効処理後の耐力を170MPa以上とすることである。

【0028】また、本発明ヘム加工用アルミニウム合金パネル材（請求項4）の要旨は、前記請求項1乃至3のいずれかの方法でフラットヘム加工されるアウトパネル材用のAl-Mg-Si系アルミニウム合金パネル材である。

【0029】なお、本発明で言うAl合金パネル材とは、熱間圧延板材、冷間圧延板材、これらを後述する調質処理（熱処理）を施した板材で、成形用の板材を含みかつ総称する。

【0030】本発明者らは、特にインナパネル材が1.0mm以下に薄板化された6000系Al合金パネル材の、しかも、アウトパネル材の縁曲部に挿入されるインナパネル材端部と縁曲部内面との間の隙間がある状態でのフラットヘム加工について、ヘム加工が優れ、かつ通常の170℃×20分の条件では勿論のこと、前記150℃×20分の低温短時間の人工時効処理（塗装焼き付け処理）条件でも170MPa以上の強度が得られる素材条件について改めて検討した。

【0031】この結果、フラットヘム加工されるアウトパネル材を、耐力を110~140MPaの範囲とし、かつ特定の成分組成範囲としたSi過剰型のAl-Mg-Si系アルミニウム合金とすれば、特にインナパネル材が1.0mm以下に薄板化された6000系Al合金パネル材であって、しかも、アウトパネル材の縁曲部に挿入されるインナパネル材端部と縁曲部内面との間の隙間がある状態でのフラットヘム加工であっても、ヘム加工性を改善でき、かつ低温での人工時効硬化能とを同時に満足する効果を有することを知見した。

【0032】この効果は、特に請求項2に記載のように、前記フラットヘム加工に先立つダウンフランジ加工における前記アルミニウム合金パネル材の90°曲げ半径を0.5~2.0の範囲とした場合に大きい。

【0033】また本発明はこのような効果を有するため、請求項3に記載のように、前記フラットヘム加工の前に6000系Al合金板材が予めプレス成形され、歪みが導入されて、ヘム加工が低下する、特に自動車アウトパネル用などのヘム加工方法に適用されて好適である。

【0034】

【発明の実施の形態】以下、本発明の好適な実施形態につき、図面を用いて説明する。まず、本発明でのフラットヘム加工方法自体は、前記図2(a)~(c)で説明したフラットヘム工程を含む従来のヘム加工と、工程および各

工程の条件も、基本的には同じである。

【0035】但し、本発明でフラットヘム加工の対象とするのは、前記した通り、Al合金アウトパネル材の板厚が0.8mm以上で、Al合金インナパネル材の板厚が1.0mm以下のものとする。Al合金アウトパネル材の板厚がこれより薄く、Al合金インナパネル材の板厚がこれより厚いものでは、本発明を用いずとも、ヘム加工性と低温での人工時効硬化能とを同時に達成することは比較的容易である。

【0036】なお、本発明でのフラットヘム加工が、Al合金パネル材の4周囲に対して全て行われるか、選択される辺（側縁部）のみに対して行われかは、部材の設計に応じて、適宜選択される。

【0037】（ダウンフランジ工程）まず、ヘム加工における、図2(a)のダウンフランジ工程は、必要により絞り工程やトリム工程等の成形加工された後のAl合金アウトパネル材1を、ダイス3aと板押さえ5aにより固定し、アウトパネル材1の縁1aを、ポンチ4aにより、直角に近い角度まで折り曲げる。

【0038】この際、アウトパネル材1の90°曲げ半径が0.5~2.0の範囲とすることが好ましい。アウトパネル材1の90°曲げ半径は、図2(a)のダイス3aの肩半径Rdおよびポンチ4aの肩半径Rpを調整して行う。

【0039】アウトパネル材の90°曲げ半径が0.5未満の場合、特にインナパネル材が1.0mm以下に薄板化された6000系Al合金パネル材であって、しかも、アウトパネル材の縁曲部に挿入されるインナパネル材端部と縁曲部内面との間の隙間がある状態でのフラットヘム加工では、本発明でのアウトパネル材の耐力規定にも関わらず、フラットヘム加工工程において、前記図3に示した割れ等の不良が生じやすくなる。

【0040】一方、アウトパネル材の90°曲げ半径が2.0を超える場合、図2(d)に示したローブヘムに近くなり、ヘム縁曲部の外観なり美観なりが損なわれる可能性が大きくなる。また、フラットヘムの縁曲部の本来の設計上の外縁線乃至外形線に対し、実際の加工後の外形線が短くなる、或いは逆に長すぎたりして、形状精度や寸法精度が出ない可能性も大きくなる。

【0041】次に、図2(b)のブリヘム工程は、ダウンフランジ工程後のアウトパネル材1を、同じく、ダイス3bと板押さえ5bにより固定し、アウトパネル材1の縁1bを、ポンチ4bにより、更に約135°の角度まで内側に折り曲げる。

【0042】更に、図2(c)のフラットヘム工程は、絞り工程やトリム工程等の成形加工後のインナパネル2の縁を、ブリヘム工程後のアウトパネル材1の縁曲げ部Aに挿入する。

【0043】この際、前記図3に示す、インナパネル材端部2aと縁曲げ部内面Aaとの間に生じる隙間tは、前記した通り、アウトパネル材1の縁曲部Aの厚みを薄く

し、曲げ条件を厳しくするため、割れ λ 等の不良を生じ易くする。したがって、この隙間 l はできるだけ小さい方がフラットヘム加工性の点で好ましい。しかし、この隙間 l を完全に無くすことはヘム加工上困難であり、また煩雑でもある。このため、本発明では、縁曲部Aの割れ λ 等の不良を生じない範囲で、ある程度の隙間 l は許容される。

【0044】この隙間 l の本発明での許容限界は、隙間 l と前記図3に示すフランジ長さ（ヘム縁曲部Aの周長） l_1 との比（ l/l_1 ）で言うと、加工条件によっても異なるが、概ね0.6以下である。しかし、従来のヘム加工では、この l/l_1 は概ね0.3程度が許容限界であった。即ち、本発明では、フラットヘム加工性の改善によって、曲げ条件を厳しくするこの隙間 l の許容限界を大きくでき、この点も本発明効果の一つである。

【0045】そして、アウトパネル材1およびインナパネル2とを、板押さえ（図示せず）とダイス3cにより固定するとともに、アウトパネル1の縁1cを、ポンチ4cにより、更に180度の角度まで内側に折り曲げフラットヘム部を形成する。このようにして、インナパネル2の縁と、アウトパネル1のフラットヘム部（縁曲部）とが接触して、両者が端部同士において接合されるとともに互いに密着される。

【0046】したがって、本発明は、従来のヘム加工工程および条件を大きく変えずに、前記二つの効果の達成が可能であるという利点も有する。

【0047】（Al合金パネル材）次に、本発明に係る、Al合金パネル材について詳細に説明する。

【0048】（耐力）まず、Al合金アウトパネル材の耐力は110～140MPaの範囲とする。図1に、後述する実施例におけるAA6016 Al合金（本発明組成）のAl合金パネル材の耐力（種々変化させた）とヘム加工性との関係を示す。図1中、白丸印はインナパネル材厚が1.0mm、黒丸印はインナパネル材厚が0.8mmの場合である。図1におけるヘム加工条件は、インナパネル板厚が0.8～1.0mmと薄く、インナパネル材端部と縁曲部内面との間に生じる隙間 l がフランジ長さ l_1 との比 l/l_1 で0.5と大きく、ダウンフランジ工程の90°曲げ半径が0.5のより厳しいフラットヘム加工とした。

【0049】図1から分かる通り、耐力が140MPaを越えた場合、特にインナパネル材が1.0mm以下に薄板化された6000系Al合金パネル材であって、しかも、前記厳しいフラットヘム加工条件では、インナパネル材厚が薄いほど（インナパネル材厚が1.0mmよりも0.8mmの場合の方が）、ヘム加工性が低下し、アウトパネル材の縁曲部に割れ等の不良が生じる。したがって、前記厳しいフラットヘム加工条件では、本発明で対象とする過剰Si型6000系Al合金パネル材では、耐力140MPa付近に、フラットヘム加工性の臨界があることが分かる。

【0050】一方、Al合金アウトパネル材の耐力が110

MPa未満では、目的とする低温時効硬化能が得られず、2%ストレッチ付与後150℃×20分の低温時効処理時の耐力が170MPa以上とならず、パネル構造体としての必要強度を満たせない。

【0051】（板厚）本発明では、前記した通り、Al合金パネル材の板厚につき、Al合金アウトパネル材の板厚は0.8mm以上で、Al合金インナパネル材の板厚は1.0mm以下のものを対象とする。Al合金アウトパネル材の板厚がこれより薄く、Al合金インナパネル材の板厚がこれより厚いものでは、板厚の効果によって、ヘム加工性が改善され、本発明の課題（ヘム加工性と低温での人工時効硬化能とを同時に達成する）は不要となる。

【0052】また、パネル材乃至パネル構造体の軽量化の点でも、Al合金インナパネル材の板厚は1.0mm以下であることが好ましい。なお、フラットヘム加工性の点からは、Al合金インナパネル材の板厚が厚い方が、逆にAl合金アウトパネル材の板厚が薄い方がヘム加工性は向上する。しかし、Al合金インナパネル材の板厚が厚くなると、パネル材乃至パネル構造体の軽量化のための、Al合金パネル材の採用自体の意義が損なわれる。

【0053】（Al合金組成）次に、本発明アウトパネル材における、化学成分組成について説明する。本発明のアウトパネルAl合金材は、過剰Si型6000系Al合金材として、特に、自動車等の輸送機のパネル構造体などとして、耐力を110～140MPaの範囲として、前記ヘム加工性や低温時効硬化能に優れ、更に、要求される、プレス成形性、耐食性、溶接性などの諸特性を兼備させる（満足する）必要がある。したがって、本発明Al合金パネル材における、Si、Mgなど各元素の含有量は、AA乃至JISの規格に規定乃至含まれるとともに、その範囲内で前記特性発揮の観点から好ましい範囲に規定される。以下に、各元素の好ましい範囲と、意義について説明する。

【0054】なお、合金元素の内、Si、Mg、Cu、Mn、以外の、Cr、Zr、Ti、B、Fe、Zn、Ni、Vなどのその他の合金元素は、基本的には不純物元素である。しかし、前記6000系合金のリサイクルの観点から、溶解材として、高純度Al地金だけではなく、6000系合金や、その他のAl合金スクラップ材、低純度Al地金などを溶解材として使用する場合を含む。このような場合には、これら他の合金元素は必然的に含まれることとなる。したがって、本発明では、目的とする前記諸特性向上効果を阻害しない範囲で、これら他の合金元素が、JIS乃至AAの規格内で含有されることを許容する。

【0055】Mg:0.4～1.2%。

Mgは、固溶強化と、塗装焼き付け処理などの人工時効処理時に、SiとともにMg/Siクラスターなどの化合物相を形成して、時効硬化能を発揮し、パネル材乃至パネル構造体として、170MPa以上の必要強度を得るための必須の元素である。

【0056】Mgの0.4%未満（質量%、以下同じ）の含有

では、絶対量が不足するため、人工時効処理時に前記化合物相を形成できず、時効硬化能を発揮できない。このためパネル材乃至パネル構造体として、170MPa以上の必要強度が得られない。

【0057】一方、Mgが1.2%を越えて含有されると、プレス成形性や曲げ加工性（ヘム加工性）等の成形性が著しく阻害される。したがって、Mgの含有量は、0.4～1.2%の範囲で、かつSi/Mgが1.0以上となるような量とするのが好ましい。

【0058】Si:0.4～1.3%。

SiはMgとともに、固溶強化と、塗装焼き付け処理などの人工時効処理時に、SiとともにMg/Siクラスターなどの化合物相を形成して、時効硬化能を発揮し、パネル材乃至パネル構造体として、170MPa以上の必要強度を得るための必須の元素である。したがって、本発明過剰Si型6000系Al合金材にあって、更に、各用途に要求される、プレス成形性、ヘム加工性、耐食性、溶接性などの諸特性を兼備させるための最重要元素である。

【0059】また、2%ストレッチ付与後150℃×20分の低温時効処理時の耐力を170MPa以上という、優れた低温時効硬化能を発揮させるためにも、Si/Mgを1.0以上とし、SiをMgに対し過剰に含有させた過剰Si型6000系Al合金組成とする。

【0060】Si量が0.4%未満では、前記時効硬化能、更に、各用途に要求される、プレス成形性、ヘム加工性、耐食性、溶接性などの諸特性を兼備することができない。

【0061】一方、Siが1.3%を越えて含有されると、特にヘム加工性や曲げ加工性が著しく阻害される。更に、溶接性を著しく阻害する。したがって、Siは0.4～1.3%の範囲とするのが好ましい。

【0062】なお、アウトパネル材では、ヘム加工性が特に重視されるため、Si含有量は0.4～1.1%と、より低めの範囲であることが好ましい。

【0063】Cu:0.1%以下、

Cuは、通常では、塗装焼き付け処理などの人工時効処理時に、Al合金材組織の結晶粒内へのMg/Siクラスターなどの化合物相を促進させる効果や、固溶したCuは成形性を向上させる効果がある。しかし、特にインナパネル材が1.0mm以下に薄板化された6000系Al合金パネル材であって、しかも、アウトパネル材の縁曲部に挿入されるインナパネル材端部と縁曲部内面との間の隙間がある状態でのフラットヘム加工では、Cuを0.1%を越えて含有すると、ヘム加工性が低下し、アウトパネル材の縁曲部に割れ等の不良が生じる。また、Cuの含有は、耐応力腐食割れ性や、塗装後の耐蝕性の内の耐食さび性、また溶接性を著しく劣化させる。このため、特に自動車アウトパネル用などのパネル材用途などの場合には、0.1%以下のできるだけ少ない量とする。

【0064】Mn:0.15%以下、

Mnには、均質化熱処理時に分散粒子（分散相）を生成し、これらの分散粒子には再結晶後の粒界移動を妨げ、Al合金組織の結晶粒を微細化させる効果がある。しかし、0.15%を越える含有では特にインナパネル材が1.0mm以下に薄板化された6000系Al合金パネル材であって、しかも、アウトパネル材の縁曲部に挿入されるインナパネル材端部と縁曲部内面との間の隙間がある状態でのフラットヘム加工では、ヘム加工性が低下し、アウトパネル材の縁曲部に割れ等の不良が生じる。したがって、Mnの含有量は0.15%以下に規制する。

【0065】Cr、Zr。

これらCr、Zrの遷移元素には、Mnと同様、均質化熱処理時に分散粒子（分散相）を生成し、微細な結晶粒を得ることができる効果がある。しかし、Cr、Zrも、0.15%を越える含有では特にインナパネル材が1.0mm以下に薄板化された6000系Al合金パネル材であって、しかも、アウトパネル材の縁曲部に挿入されるインナパネル材端部と縁曲部内面との間の隙間がある状態でのフラットヘム加工では、ヘム加工性が低下し、アウトパネル材の縁曲部に割れ等の不良が生じる。したがって、Cr、Zrの含有量も0.15%以下に規制することが好ましい。

【0066】Ti、B。

Ti、Bは、Ti:0.1%、B:300ppmを各々越えて含有すると、粗大な晶出物を形成し、成形性を低下させる。但し、Ti、Bには微量の含有で、鋳塊の結晶粒を微細化し、プレス成形性を向上させる効果もある。したがって、Ti:0.1%以下、B:300ppm以下までの含有は許容する。

【0067】Fe。

溶解材から混入して、不純物として含まれるFeは、Al₃Cu₂Fe、Al₃(Fe、Mn)₂Cu₂、(Fe、Mn)Al₃などの晶出物を生成する。これらの晶出物は、破壊靱性および疲労特性更にはヘム加工性などの成形性を著しく劣化させる。特に、Feの含有量が0.50%を越えると顕著にこれらの特性が劣化するため、好ましくは、Feの含有量（許容量）を0.50%以下のできるだけ少ない量とすることが好ましい。

【0068】Zn。

Znは0.1%を越えて含有されると、耐蝕性が顕著に低下する。したがって、Znの含有量は好ましくは0.1%以下のできるだけ少ない量とすることが好ましい。

【0069】また、本発明のインナパネル材の材質は上記アウトパネル材と同じ材質でも良く、また異なっても良い。アウトパネル材とインナパネル材とを同じ材質のAl合金材として調達やリサイクルの利便性を図るユニアロイ化の観点からは前記アウトパネル材と同じ過剰Si型の6000系Al合金材が好ましい。ただ、自動車等の輸送機のパネル構造体などとしてのインナパネル材には、プレス成形性以外には、上記アウトパネル材のような厳しい要求諸特性を兼備させる必要はない。このため、前記ア

ウタパネル材と同じでなくとも、AA乃至JISの3000系、Al-Mg系5000系、6000系などのプレス成形性に優れたAl合金材が適宜使用できる。

【0070】(製造方法)以上の組成からなる、本発明における過剰Si型6000系Al合金アウタパネル材およびインナパネル材は、常法により製造が可能である。但し、アウタパネル材には、前記した通り、要求諸特性を兼備させる必要から、常法による各工程においても、各々好ましい製造条件があり、この点を含め以下に説明する。

【0071】溶解、鋳造工程では、本発明成分規格範囲内に溶解調整された、過剰Al合金溶湯を、連続鋳造圧延法、半連続鋳造法(DC鋳造法)等の通常の溶解鋳造法を適宜選択して鋳造する。

【0072】次いで、このAl合金鋳塊に均質化熱処理を施した後、熱間圧延-冷間圧延(必要により、熱延-冷延の間、冷延の間にパッチ式あるいは連続式の中間焼鈍なども施しながら)を行い、コイル状、板状などのパネル材の形状に加工する。

【0073】加工後のAl合金材は、調質処理として、まず、必須に溶体化および焼入れ処理(T4処理)される。溶体化および焼入れ処理は、後の塗装焼き付け硬化処理などの人工時効処理によりMg/Siクラスターや β'' 相などの化合物相を十分粒内に析出させるために重要な工程である。この効果を出すための溶体化処理条件は、500~550℃の温度範囲で行うのが好ましい。

【0074】但し、ヘム加工性が特に重視されるパネル材の場合には、溶体化処理条件は、500~530℃のより低温側の方が好ましい。

【0075】溶体化処理後の焼入れの際、冷却速度は300℃/分以上の急冷とすることが好ましい。冷却速度が300℃/分未満の遅い場合には、焼入れ後の強度が低くなり、時効硬化能が不足し、後の塗装焼き付け硬化処理などの人工時効処理により、170MPa以上の高耐力を確保できない。

【0076】また、溶体化後の焼き入れ時に粒界上にSi、MgSiなどが析出しやすくなり、プレス成形やヘム加工時の割れの起点となり易く、これら成形性が低下する。この冷却速度を確保するために、焼入れ処理は、ファンなどの空冷でもよいが、ミスト、スプレー、浸漬等の水冷手段から選択して行うことが好ましい。

【0077】溶体化焼入れ処理後、室温時効抑制の原因となるSi-空孔、Si/空孔クラスター自体の生成を抑制するために、予備時効処理をすることが好ましい。即ち、50~100℃の温度範囲に、1~24時間の必要時間保持することが好ましい。また、予備時効処理後の冷却速度は、1℃/hr以下であることが好ましい。

【0078】この予備時効処理として、溶体化処理後の焼入れ終了温度を50~100℃と高くした後に、直ちに再加熱乃至そのまま保持して行う。あるいは、溶体化処理後常温までの焼入れ処理の後に、直ちに50~100℃に再

加熱して行う。

【0079】また、連続溶体化焼入れ処理の場合には、前記予備時効の温度範囲で焼入れ処理を終了し、そのままの高温でコイルに巻き取るなどして行う。なお、コイルに巻き取る前に再加熱しても、巻き取り後に保温しても良い。また、常温までの焼入れ処理の後に、前記温度範囲に再加熱して高温で巻き取るなどしてもよい。

【0080】

【実施例】次に、本発明の実施例を説明する。

(実施例I)まず、アウタパネル材用の過剰Si型6000系Al合金として、AA 6016 Al合金規格組成のAl合金板を、溶体化処理条件を変え、また、前記予備時効処理を選択的にを行い、耐力を110~140MPaの本発明範囲内のもの、この範囲から外れたものと種々変えて作成した。このAA 6016 Al合金組成を表1のNo.1、2に示す。比較のために、本発明範囲を外れた合金組成の過剰Si型乃至過剰Mg型6000系Al合金板も準備した。これらのAl合金組成も表1のNo.3、4、5に示す。また、発明例、比較例のAl合金板の板厚と調質処理後の耐力を表2に示す。

【0081】Al合金板の作成は以下の条件とした。Al合金の50mm鋳塊を、DC鋳造法により溶製後、550℃×4時間の均質化熱処理を施し、480℃以下の温度で厚さ5mmまで熱間圧延した。この熱間圧延板を、昇温速度40℃/hrで500℃×30秒の条件で焼鈍処理を行い、その後、厚さ0.8、1.0mmまで冷間圧延した。この冷延板を、更に熱処理炉において、500~550℃の範囲で溶体化処理条件を変えて、処理を行った後、直ちに水冷乃至空冷による焼入れを行うT4調質処理を行った。

【0082】前記焼入れの際の冷却速度は50~600℃/分の範囲で調整し、焼入れ終了温度(焼入れ温度)は共通して80℃とし、焼入れ後にこの温度で2時間保持する予備時効(保持後の冷却速度1℃/hr以下)を行った。

【0083】これらのAl合金板からヘム加工試験用の短冊状供試板(ブランク)を複数枚切り出し、このブランクに対し、ヘム加工に先立ち、まず、自動車ドアのアウタパネルの絞りトリム工程等の成形加工を模擬して、5%の歪みを予め与えた。そして、ブランクのフラットヘム加工代(ヘム加工後のアウタパネルブランクの、内側に折り曲げられた端部から折り曲げ部の端部までの距離)を12mmとして、以下のヘム加工を行った。

【0084】まず、前記図2(a)に示したダウンフランジ工程によって、歪みを予め与えたブランク(アウタパネル)の縁を、90度の角度となるまで折り曲げた。この際、Al合金パネル材の90°曲げ半径を0.5~1.0と変えた。90°曲げ半径の調整は、ダイス3aの肩半径Rdにて行った。これらAl合金パネル材の90°曲げ半径を表2に示す。

【0085】次に、図2(b)に示したブリヘム工程によって、ブランクの縁を更に135°の角度まで内側に折り曲げた。

【0086】その後、同じく前記Al合金板から切り出し、インナパネルとしてのブランク（アウトパネル材であるAA 6016 Al合金と同じパネル材、板厚0.8～1.0mm）の縁を、前記ブランク（アウトパネル）の折り曲げ部に挿入して、インナパネル材端部と縁曲げ部内面との間に生じる隙間 l を設け、更に図2(c)に示したフラットヘム工程によってフラットヘムを設けた。これらインナパネルの板厚と前記隙間 l を表2に示す。但し、隙間 l はフランジ長さ l との比 l/l で示す。

【0087】そして、フラットヘムの縁曲部の、肌荒れ、微小な割れ、大きな割れの発生などの表面状態を目視観察した。評価は、1:肌荒れや微小な割れも無く良好、2:肌荒れが発生しているものの、微小なものを含めた割れはない、3:微小な割れが発生、4:大きな割れが発生、5:大きな割れが複数乃至多数発生、の5段階の評価をした。この評価として、ヘム加工性が良好（使用可）と判断されるのは1～2段階までで、3段階以上はヘム加工性が劣る（使用不可）と判断される。

【0088】更に、製造後の前記Al合金板を、2%ストレッチ付与後150℃×20分の低温短時間で人工時効硬化処理した後の耐力（BH耐力、ベークハード耐力）を測定し、低温時効処理能を調査した。これらの結果を前記フラットヘム加工性と併せて表2に示す。

【0089】表2から明らかな通り、110～140MPaの本発明耐力範囲内で、かつ本発明過剰Si型6000系Al合金組成範囲内のアウトパネル材（表1のNo.1、2のAl合金）を用いた発明例No.1～6は、インナパネル板厚が0.8mmと薄く、インナパネル材端部と縁曲げ部内面との間に生じる隙間 l が大きく、かつダウンフランジ工程の90°曲げ半径が0.5の厳しいヘム加工であっても、ヘム加工性が優れ、かつ150℃×20分の低温短時間で人工時効硬化処理した後のBH耐力が170MPa以上あることが分かる。 *

*【0090】しかし、本発明過剰Si型6000系Al合金組成範囲内のアウトパネル材（表1のNo.1、2のAl合金）であっても、耐力が140MPaの本発明上限を越えて高い比較例7は、インナパネル板厚が0.8mmと薄く、インナパネル材端部と縁曲げ部内面との間に生じる隙間 l が大きく、ダウンフランジ工程の90°曲げ半径が0.5の厳しいヘム加工では割れが生じている。また、特に耐力が152MPaとより高い比較例8はインナパネル板厚を1.0mmと厚く、インナパネル材端部と縁曲げ部内面との間に生じる隙間 l を小さく、かつダウンフランジ工程の90°曲げ半径を1.0と大きくして、ヘム加工条件を緩和しても割れが生じている。

【0091】更に、本発明過剰Si型6000系Al合金組成範囲内のアウトパネル材（表1のNo.1、2のAl合金）であっても、耐力が110MPaの本発明下限より低い比較例9、10は、ヘム加工では割れが生じていないものの、150℃×20分の低温短時間で人工時効硬化処理した後のBH耐力は170MPaを満たさない。

【0092】また、耐力が本発明範囲内であっても、本発明過剰Si型6000系Al合金組成範囲から外れる（表1のNo.3、4、5のAl合金）アウトパネル材を用いた比較例11、12、13は、インナパネル板厚を1.0mmと厚く、インナパネル材端部と縁曲げ部内面との間に生じる隙間 l を小さく、かつダウンフランジ工程の90°曲げ半径を1.0と大きくして、ヘム加工条件を緩和しても割れが生じている。

【0093】以上の結果から、本発明における、本発明過剰Si型6000系Al合金組成と耐力のフラットヘム加工性と低温時効処理能からの臨界的な意義が分かる。

【0094】

【表1】

番号	Al合金板の化学成分（質量%、但しBはppm、残部Al）										備考
	Si	Fe	Cu	Mn	Mg	Cr	Zn	Zr	Ti	B	
1	1.1	0.25	0.05	0.05	0.5	-	-	-	0.01	30	6016
2	0.85	0.25	0.05	0.05	0.6	-	-	-	0.01	30	6001
3	0.65	0.25	0.15	0.05	1.0	0.15	-	-	0.01	30	6061
4	0.85	0.25	0.05	0.5	0.6	-	-	-	0.01	30	6001
5	1.1	0.25	0.20	0.05	0.5	-	-	-	0.01	30	6016

適用	番号	合金番号	アウト材		ヘム加工			ヘム曲部	特性
			耐力 MPa	板厚 mm	90° 曲 げ半径	イン ナ板 厚mm	インナ 先端隙 間t/l	表面状態 (割れの 有無)	
発 明 例	1	1	112	1.0	0.5	0.8	0.5	1	172
	2	1	124	1.0	0.5	0.8	0.5	1	180
	3	1	138	1.0	0.5	0.8	0.5	1	183
	4	2	110	1.0	0.5	0.8	0.5	1	173
	5	2	125	1.0	0.5	0.8	0.5	1	178
	6	2	138	1.0	0.5	0.8	0.5	1	181
比 較 例	7	1	143	1.0	0.5	0.8	0.5	3	188
	8	1	152	1.0	1.0	1.0	0.2	5	190
	9	1	105	1.0	0.5	0.8	0.5	1	160
	10	2	107	1.0	0.5	0.8	0.5	1	162
	11	3	129	1.0	1.0	1.0	0.2	3	172
	12	4	134	1.0	1.0	1.0	0.2	4	175
	13	5	133	1.0	1.0	1.0	0.2	4	175

【0096】

【発明の効果】本発明によれば、ヘム加工性と低温での人工時効硬化能とを同時に満足する、Al合金パネル材のヘム加工方法およびヘム加工用Al合金パネル材を提供することができる。したがって、Al合金材の自動車などの輸送機などへの用途の拡大を図ることができる点で、多


【図面の簡単な説明】

*【図1】本発明に係るAl合金パネル材のダウンフランジ加工におけるヘム加工性と耐力との関係を示す説明図である。


【図2】ヘミング加工の概要を示し、(a)はダウンフランジ工程、(b)はプリヘム工程、(c)はフラットヘム工程、(d)はローブヘム工程を示す説明図である。

【図3】フラットヘム加工におけるアウトパネル材の縁曲部を示す斜視図である。


【図1】



【図3】



【図2】



フロントページの続き

(51) Int. Cl. ⁷	識別記号	F I	テコード (参考)
C 2 2 F 1/05		C 2 2 F 1/05	
// C 2 2 F 1/00	6 0 2	1/00	6 0 2
	6 2 3		6 2 3
	6 3 0		6 3 0 A
			6 3 0 K
	6 9 1		6 9 1 B
			6 9 1 C
	6 9 4		6 9 4 A